

Technical Datasheet Cello Supernatural Classic

Mühlbacher Straße 1 01561 Lampertswalde/Dresden Tel. +49 3522 33-30 · Fax +49 3522 33-399 www.krono-original.com · info@kronoflooring.com

Direct Pressure Laminate, Level of use according to EN 13329: class 23/32 - AC4

Heavy domestic use Commercial general use					
DIMENSION					
dimension	thickness (d)	8 ± 0,50 mm · dmax - dmin ≤ 0		≤ 0,50 mm	
	length	1285 ± 0,50 mm			
	width (b)	192 ± 0,10 mm ⋅ bmax - bmin		≤ 0,20 mm	
profile	long side	twin clic	short side	1clic2go	
groove	long side	real groove	short side	real groove	
TOLERANCE					
squareness		EN 13329		≤ 0,20 mm	
straightness		EN 13329		≤ 0,30 mm	
flatness crosswise		EN 13329		concave: ≤ 0,15% · convex: ≤ 0,20%	
flatness length		EN 13329		concave: ≤ 0,50% · convex: ≤ 1,00%	
gaps between elements		EN 13329		average: ≤ 0,15 mm · max: ≤ 0,20 mm	
height difference between elements		EN 13329		average: ≤ 0,10 mm · max: ≤ 0,15 mm	
misalignment				± 2 mm	
TEST					
abrasion resistance		EN 13329		AC4 (≥ 4000 rpm)	
impact resistance		EN 13329		small ball ≥ 12 N · big ball ≥ 750 mm	
stain resistance	group 1 & 2	EN 13329			grade 5
	group 3				≥ grade 4
castor chair test		EN 13329		no change in appearance or damage, as defined per EN 425	
effect of a furniture leg		EN 13329		no damage shall be visible, when testet with foot type 0	
thickness swelling		EN 13329		≤ 18%	
static indentation		EN 13329		≤ 0,05 mm	
light fastness		EN 13329		grey scale ≥ 4 at blue wool grade 6	
dimensional variations after changes in relative humidity		EN 13329		lengthwise ≤ 0,9 mm · crosswise ≤ 0,9 mm	
locking strength		EN 13329		length ≥ 1 kN/m · width ≥ 2 kN/m	
surface soundness		EN 13329		≥ 1,25 N/mm²	
ENVIRONMENT					
emission of formaldehyd	de	EN 717-1			Klasse E1
PHYSICAL BEHAVIOR					
fire behavior		EN 13501-1		Cfl s1	
slide resistance		EN 13893		technical class DS	
thermal resistance thermal conductivity		EN 12667		0,073 (m²K)/W ± 15%	
thermal conductivity		EN 12664		0,110 W/(m*K) ± 15%	