

## TECHNICAL DATA SHEET 08-2018

### DIMENSIONS

#### FORMAT

Width	190,5	mm
Length	1257	mm
Number of panels per pack	9	
m <sup>2</sup> per pack	2,1551	m <sup>2</sup>
Bevels	V-groove on all sides	
Thickness	8,0	mm
Tongue and groove	Drop Down	

### FACTORY WARRANTY

	METHOD	PARAMETERS	Values
Usage class	EN 13329		Class 21-22-23/31-32*
CE	EN 14041	Notified body	NB0766 EPH Dresden RAW-Dop-8mm-U-052018
Warranty	Residential use Commercial use	See warranty conditions See warranty conditions	20 years On request

### GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS	Values
Wear resistance	EN 13329		≥ 4000 cycles	* with overlay class 32
Wear class	EN 13329		AC4	* with overlay AC4
Impact resistance	EN 13329		IC2	IC2
Scratch resistance	EN 438-2, 25		Charge ≥ 3N	Charge ≥ 5N
Effect of a castor chair	ISO 4918 (with underlay)	Type W (EN 12529)	25000 cycles	No change
Thickness swelling	ISO 24336	After 24h immersion at 20°C	≤ 18%	≤ 12%
Locking strength	ISO 24334	F10,2 long side	≥ 1 kN/m	≥ 1 kN/m
		Fmax long side		≥ 1 kN/m
		Fs0,2 short side	≥ 2 kN/m	≥ 2 kN/m
		Fmax short side		≥ 2 kN/m
Effect of a furniture leg	EN 424		No damage shall be visible, when tested with foot type 0	No visible damage
Surface soundness	EN 13329	N/mm <sup>2</sup>	≥ 1,25	≥ 1,50
Static indentation	EN 433		residual indentation ≤ 0,05 mm	No visible change
Resistance to staining	EN 438	Group 1,2	Class 5	Class 5
		Group 3	Class 4	Class 5
General appearance	EN 13329	Height differences	≤ 0,15 mm	≤ 0,10 mm
		Opening between joints	≤ 0,20 mm	≤ 0,10 mm
		Cupping in the length	concave ≤ 0,50%	≤ 0,50%
			convex ≤ 1,00%	≤ 1,00%
		Cupping in the width	concave ≤ 0,15%	≤ 0,15%
convex ≤ 0,20%	≤ 0,20%			
Dimensional variations after changes in relative humidity	EN 13329	δl	δl average ≤ 0,9 mm	≤ 0,9 mm
		δw	δw average ≤ 0,9 mm	≤ 0,9 mm
Light fastness	EN ISO 105 B02	Blue reference	Class ≥ 6	Class 8

### OTHER TECHNICAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	Values
Impact sound reduction	ISO 712/2			ΔLw ≈ 18 dB (Depending on used underlay)
Burning cigarette	EN 438-2,30		Class 4	Class 5

### ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	Values
Formaldehyde emission	EN 717-1	ppm	E1 < 0,1	< 0,01
Anti-static	EN 1815		≤ 2,0 kV	≤ 2,0 kV
Reaction to fire	EN 13501-1	Class		Cfl-s1
Thermal resistance	EN 12996:2001	m <sup>2</sup> K/W		0,055 m <sup>2</sup> K/W
Floor heating			See special instructions	Suitable
Slip resistance	EN 13893	μ	μ ≥ 0,30	DS: μ ≥ 0,30

