## MATERIALS SAFETY DATA SHEET

## IDENTIFICATION OF PRODUCT AND COMPANY

Product name : Monotub DD Column Former Ø150mm - Ø1200mm (various lengths) Product description : Heat sealed and spirally wound PE coated paper, as supplied by TP

Supplier information: Nevoga s.r.o.

Kotkova 22

66902 Znojmo, Czech Republic

Tel. +420 - 515282821 Fax. +420 - 515220070

## **COMPOSITION / INFORMATION ON INGREDIENTS**

Polyethylene

• Printing ink (NOT containing heavy metals, such as Pb, Cd, Cr, Hg)

Paperboard

• Aluminium Foil (food approved quality)

• Polyethylene copolymer

• Recycled Grey Cardboard

#### **HAZARDS IDENTIFICATION**

Health hazardous components : NONE Environmental hazardous components : NONE

Fire hazardous components : Kraft liner, Grey Cardboard, Polyethylene

#### FIRST AID MEASURES

Inhalation : first aid is normally not required Skin contact : first aid is normally not required Eye contact : first aid is normally not required Indigestion : first aid is normally not required

# FIRE FIGHTING MEASURES

## Fire fighting procedures:

- Use water spray to cool fire exposed surfaces and to protect personnel. Block the supply to the fire.
- Extinguishing Media: WATER, CARBON DIOXIDE, DRY CHEMICAL

## Special fire precautions:

• Respiratory and eye protection required for fire fighting personnel.

#### Specific hazards:

- Classed as flammable. Combustion will evolve toxic and irritating vapours.
- Unusual Fire/Explosion Hazard: NONE

#### ACCIDENTAL RELEASE MEASURES

N.A.

## HANDLING AND STORAGE

Storage temperature : between +5 and +40 0C Transport temperature : between -18 and +40 0C Loading/unloading temperature : between -18 and +40 0C

Viscosity : N.A. Electrostatic accumulation : N.A.

Usual shipping form : several diameters per full truck (loose stacked)

Storage / handling, general notes

- Handle Column Formers with care.
- DO NOT handle, store or unload near an open flame, sources of heat or sources of ignition. Store in a dry place.
- Special attention should be paid to avoid inappropriate storage of Column Formers.

## **EXPOSURE CONTROLS / PERSONAL PROTECTION**

No occupational exposure limits assigned. The handling of this product does not require special forms of personal protection.

NEVOGA s.r.o. COLUMN FORMERS ARE ARTICLES WHICH UNDER NORMAL CONDITIONS OF USE, DO NOT POSE ACUTE OR CHRONIC HEALTH HAZARDS.

# PHYSICAL AND CHEMICAL PROPERTIES

PE Melting point : between 130-145 °C

Molecular formula :  $[C_2 H_4]n$  (typical molecular weight 100,000 - 500,000)

CAS No : 9002-88-4

Vapour Pres : NA.
Vapour Density : N.A.
Spec Gravity : N.A.
PH : N.A.
Evaporation Rate & Reference : N.A.

Solubility in Water : INSOLUBLE Appearance and Odour : ODOURLESS

Percent Volatiles by Volume : N.A.

For further information, see our product specifications

#### STABILITY AND REACTIVITY

Polyethylene coating is stable, but breaks down slowly in UV light or sunlight. Materials to avoid are oxidizing acids, chlorinated/non-chlorinated hydrocarbons and solvents. Stability Condition to avoid: N.A.

UPON HEATING TO EXTREME HIGH TEMPS, THE PRODUCT MAY EMIT IRRITATING VAPOURS.

#### TOXICOLOGICAL INFORMATION

#### Inhalation

- Vapours formed at elevated temperatures may cause irritation to eyes and respiratory tract
- Negligible hazard at ambient temperature (-18 to 40 0C)

#### Skin contact

- Exposure to hot material may cause thermal burns
- Negligible hazard at ambient temperature (-18 to 40 0C)

### Eye contact

• Particulates may scratch eye surfaces or cause mechanical irritation

### Indigestion

Minimal toxicity

## **ECOLOGICAL INFORMATION**

Solubility : the product is insoluble in water

Ecotoxicity : no data

Environmental degradability: No acute toxicity to aquatic and/or terrestrial organisms

### **DISPOSAL CONSIDERATIONS**

In accordance with Federal, State and Local regulations. Suitable routes of disposal are incineration in appropriate incinerators with energy recovery, disposal in landfills or appropriate recycling methods.

CO<sub>2</sub> emissions from different fuels

Category of fuel	Energy contents MJ/kg	Thermal efficiency	Gross CO <sub>2</sub> emission kg/kg	Fossil fuel %	Real contribution to CO <sub>2</sub> enrichment of atmosphere kg/ MJ	Ratio
Oil	41.0	0.9	3.1	100	0.084	1
Coal	28.5	0.8	3.0	100	0.132	1.57
Tetra Brik waste	21.6	0.8	1.9	33	0.036	0.42
Household waste	10.0	0.8	0.9	41	0.046	0.54

Source: G. Sundström AB, Malmö, Sweden

#### TRANSPORT INFORMATION

Land : this product is not regulated for road/rail transport

Inland waterways : this product is not regulated for inland waterways transport

Sea : this product is not regulated for sea transport
Air : this product is not regulated for air transport

#### REGULATORY INFORMATION

N.A.

#### OTHER INFORMATION

This information relates only to the specific material designated and may not be valid for such material in combination with any other materials or in any process other than usual. Such information is to the best of Van Antwerpen Cartonnage BV's knowledge and believed accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use.