



DATA SHEET

N°20/NG08 - R. 01 - 10/5/2012

Mod. 03 PGQ 5.4_01 Rev. 01 del 03.09.2007

0799-CPD

GEO PP 2NG/08


Geo&tex 2000 S.p.A., Via XXV Aprile 3, I-36020 SAN NAZARIO (VI), Italy
Produced in factories 16166 - A, 16166 - B

12

0799 - CPD - 15





Non woven Geotextile manufactured from UV-stabilised polypropylene staple fiber, needlepunched and thermocalendered

suitable for the following applications:

☒		EN 13249:2000+A1:2005 : Characteristics required for use in the construction of roads and other trafficked areas	☒		EN 13250:2000+A1:2005 : Characteristics required for use in the construction of railways
☒		EN 13251:2000+A1:2005 : Characteristics required for use in earthworks, foundations and retaining structures	☐		EN 13252:2000+A1:2005 : Characteristics required for use in drainage systems
☒		EN 13253:2000+A1:2005 : Characteristics required for use in erosion control works (coastal protection, bank revetments)	☒		EN 13254:2000+A1:2005 : Characteristics required for use in the construction of reservoirs and dams
☒		EN 13255:2000+A1:2005 : Characteristics required for use in the construction of canals	☐		EN 13256:2000+A1:2005 : Characteristics required for use in the construction of tunnels and underground structures
☒		EN 13257:2000+A1:2005 : Characteristics required for use in solid waste disposal	☒		EN 13265:2000+A1:2005 : Characteristics required for use in liquid waste containment projects

Functions:

F - R - F+R+S - F+S - R+S - F+R

☒ 	☒ 	☐ 	☐ 	☒ 
---	---	--	--	---

Characteristic	Test Method	Unit		Nominal Value	Tolerance
Mass per unit area	EN ISO 9864	g/m ²		140	-17
Thickness	EN ISO 9863-1	mm	2 kPa	NR	NR
Wide-Width Tensile Strength	EN ISO 10319	kN/m	MD	10,50	-1,00
			CMD	11,50	-1,00
			DIAGONAL	NR	NR
Elongation	EN ISO 10319	%	MD	40	-8 / +25
			CMD	54	-10,8 / +30
			DIAGONAL	NR	NR
Energy Index	EN ISO 10319	kN/m		≥2,1	NR
Static Puncture Resistance	EN ISO 12236	N		1600	-160
Dynamic Perforation Test	EN ISO 13433	mm		30,00	+ 6,00
Pyramidal Puncture Resistance	NF G 38019	kN		NR	NR
Characteristic Opening Size	EN ISO 12956	µm		80	-24 / +24
Permeability normal to the Plane	EN ISO 11058	m/s		0,060	-0,018
Long Term Protection Efficiency	EN 13719	%	300 kPa	NR	NR
			600 kPa	NR	NR
			1200 kPa	NR	NR
Water Flow Capacity in the Plane	EN ISO 12958	m ² /s	20 kPa - i=1	NR	NR
			100 kPa - i=1	NR	NR
			200 kPa - i=1	NR	NR
Durability Prediction	To be covered within 1 month after installation. Predicted to be durable for more than 80 years in natural soils with 4<ph<9 and soil temperature < 15 °C (Ass essment 325070/110701)				
Oxidation Resistance	EN ISO 13438	Residual Strength		MD	>90%
				CMD	>90%
Chemical Resistance	EN 14030	Residual Strength		MD	>90%
				CMD	>90%
Microbiological Resistance	EN 12225	Residual Strength		MD	100%
				CMD	100%


MD : Machine Direction - CMD : Cross Machine Direction - NR : Not Required for application

TOLERANCE ON ROLL WIDTH: ± 3 cm. TOLERANCE ON ROLL LENGTH: ± 2% IF LENGTH ≤ 200 m, ± 1% IF LENGTH > 200 m.

STANDARD CORES: PAPER, DIAMETER INNER 81mm / OUTER 89mm ± 5%. TOLERANCE ON GROSS/NET WEIGHT ± 5%.

TECHNICAL DATA BASED ON STATISTIC ANALYSIS ON 95% CONFIDENCE LIMIT. PRESENT DATA SHEET CAN BE MODIFIED WITHOUT PRIOR NOTICE

Date	Issued	COM
10/05/2012		

Date	Verified	RCO
10/05/2012		

Date	Approved	RSO
10/05/2012		