










INFORMAZIONI TECNICHE

TECHNICAL FEATURES / INFORMATIONS TECHNIQUES / TECHNISCHE INFORMATIONEN / INFORMACIÓN TÉCNICA

DESCRIZIONE DESCRIPTION / DESCRIPTION BESCHREIBUNG / DESCRIPCIÓN	NORME REGULATION / NORME / NORM / NORMA EN 14411 - ISO 13006	REQUISITI PRESCRITTI REQUIRED VALUES / EXIGENCES RÉGLEMENTAIRES / VORGESCHRIEBENE ANFORDERUNGEN / REQUISITOS ESTABLECIDOS	VALORI VALUES / VALEURS WERTE / VALORES		
 DIMENSIONI RETTIFICATO SIZES RECTIFIED / FORMAT RECTIFIÉ / ABMESSUNGEN NACH DEM SCHLEIFEN / TAMAÑO RECTIFICADO	UNI EN ISO 10545-2	lunghezza-larghezza ±0,3% (±1,0 mm max) <i>length-width / longueur-largeur / Länge-Breite / longitud-ancho</i>	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME		
		spessore ±5,0% (±0,5 mm max) <i>thickness / épaisseur / Stärke / espesor</i>			
ortogonalità ±0,3% (±1,5 mm max) <i>rectangularity / orthogonalité / Rechtwinkligkeit / ortogonalidad</i>					
rettilinearità ±0,3% (±0,8 mm max) <i>straightness / rectilignité / Geradlinigkeit / rectilineidad</i>					
planarità ±0,4% (±1,8 mm max) <i>surface flatness / planéité / Ebenflächigkeit / planaridad</i>					
qualità superficie ≥95% <i>surface quality / qualités surface / Oberflächenbeschaffenheit / cualidades superficie</i>					
DIMENSIONI NON RETTIFICATO SIZES NOT RECTIFIED / FORMAT NON RECTIFIÉ / ABMESSUNGEN VOR DEM SCHLEIFEN / TAMAÑO NO RECTIFICADO	UNI EN ISO 10545-2	lunghezza-larghezza ±0,6% (±2,0 mm max) <i>length-width / longueur-largeur / Länge-Breite / longitud-ancho</i>	-		
		spessore ±5,0% (±0,5 mm max) <i>thickness / épaisseur / Stärke / espesor</i>			
ortogonalità ±0,5% (±2,0 mm max) <i>rectangularity / orthogonalité / Rechtwinkligkeit / ortogonalidad</i>					
rettilinearità ±0,5% (±1,5 mm max) <i>straightness / rectilignité / Geradlinigkeit / rectilineidad</i>					
planarità ±0,5% (±2,0 mm max) <i>surface flatness / planéité / Ebenflächigkeit / planaridad</i>					
qualità superficie ≥95% <i>surface quality / qualités surface / Oberflächenbeschaffenheit / cualidades superficie</i>					
 ASSORBIMENTO ACQUA WATER ABSORPTION / ABSORPTION D'EAU / WASSERAUFNAHME / ABSORCIÓN DE AGUA	UNI EN ISO 10545-3	≤0,5%	≤0,1%		
 RESISTENZA A ROTTURA BREAKING STRENGTH / RÉSISTANCE À LA RUPTURE / BRUCHFESTIGKEIT / RESISTENCIA A LA ROTURA	UNI EN ISO 10545-4	R≥35 N/mm² S≥700 N (<7,5 mm) S≥1300 N (≥7,5 mm)	6 mm R≥40 N/mm² S≥1000 N	9 mm R≥40 N/mm² S≥1500 N	20 mm R≥45 N/mm² S≥10000 N
 RESISTENZA ABRASIONE PROFONDA (UGL - Matt) DEEP ABRASION RESISTANCE (UGL - MATT) / RESISTANCE À L'ABRASION PROFONDE (UGL - MATT) / TIEFENVERSCHLEISSBESTÄNDIGKEIT (UGL - MATT) / RESISTENCIA A LA ABRASIÓN PROFUNDA (UGL - MATT)	UNI EN ISO 10545-6	≤175 mm ³	≤150 mm ³		
 RESIST. ABRASIONE SUPERFICIALE (GL - Lappato / Silky) SURFACE ABRASION RESISTANCE (GL - LAPPATO / SILKY) / RESIST. A L'ABRASION SUPERFICIELLE (GL - RODÉ / SILKY) / WIDERSTÄNDIGKEIT GEGEN OBERFLÄCHENVERSCHLEISS (GL - GELÄPPT / SILKY) / RESIST. ABRASIÓN SUPERFICIAL (GL: ESMALTADO / SILKY)	UNI EN ISO 10545-6	dichiarare un valore / declare a value / déclarer une valeur / einen Wert angeben / declarar un valor	-		
 RESISTENZA SHOCK TERMICI THERMAL SHOCK RESISTANCE / RESISTANCE AUX ÉCARTS DE TEMPÉRATURE / WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN / RESISTENCIA A LOS CAMBIOS DE TEMPERATURA	UNI EN ISO 10545-9	resistenza / resistant / résistance / Widerständigkeit / resistencia	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME		
 RESISTENZA AL GELO FROST RESISTANCE / RESISTANCE AU GEL / FROSTWIDERSTANDSFÄHIGKEIT / RESISTENCIA AL HIELO	UNI EN ISO 10545-12	resistenza / resistant / résistance / Widerständigkeit / resistencia	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME		
 RESISTENZA CHIMICA CHEMICAL RESISTANCE / RESISTANCE CHIMIQUE CHEMISCHE BESTÄNDIGKEIT / RESISTENCIA QUÍMICA	UNI EN ISO 10545-13	resistenza / resistant / résistance / Widerständigkeit / resistencia	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME		
 RESISTENZA ALLE MACCHIE STAIN RESISTANCE / RESISTANCE AUX TACHES / FLECKENFESTIGKEIT / RESISTENCIA A LAS MANCHAS	UNI EN ISO 10545-14	pulibile / cleanable / nettoyyable / kann gereinigt werden / lavable	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME		
	DIN 51130	R	R9 120x278 - 120x120 - 60x120 - 30x120 - 80x80 - 60x60 - 30x60 - 9,7x60 R10 60x120 - 60x60 - 30x60 R11 60x90 K2 - 80x80 K2		
	DIN 51097	A+B+C	A Natural R9 A+B Structured R10 A+B+C Structured R11		
	B.C.R.A. (COF)	>0,40 bagnato / wet	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME		
	ANSI A137.1 2012 (DCOF)	>0,42 bagnato / wet	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME		
	BS 7976-2:2002 (UK) (Pendulum Test Value)	0-24 scivoloso / <i>slippery / glissant / Rutschig / resbaladizo</i> 25-35 scivolosità moderata / <i>moderately slippery / glissance modérée / mäßige</i> <i>Rutschgefahr / Deslizamiento moderado</i> >36 basso rischio scivolamento / <i>low slipping risk / risque de glissement faible / geringe</i> <i>Rutschgefahr / bajo riesgo de deslizamiento</i>	>36 60x120 - 60x60 - 30x60 White/Ivory/Gold/Avana		

Piastrelle pressate a secco - Conforme alla norma EN 14411 e ISO 13006 appendice G gruppo B1-a con E ≤0,5%

Dry pressed tiles - Compliant with standards EN 14411 and ISO 13006 annex G group B1-a with E ≤0,5% / Carreau pressé à sec - Conforme à la norme EN 14411 et ISO 13006 annexe g groupe B1-a avec E ≤0,5% / Trocken gepresste Fliesen - Erfüllen die Anforderungen der Norm en 14411 und ISO 13006 Anhang G Gruppe B1-a mit E ≤0,5% / Baldosas prensadas en seco - Conforme a las normas en 14411 e iso 13006, anexo g grupo B1-a con E ≤0,5 %