



WOOD

Tango



Product
Datasheet
2011

WOOD

Tango



TECHNICAL INFORMATION	TANGO
Thickness	13 mm
Width	117/162/190
Length	1075/1245/2000/ 2200
Wearlayer thickness (mm)	app. 2,5
Weight (kg/m ²)	app. 7,2
Taber Abraser/Lacquer's wear resistance* prEN 13696	
abrasion penetration Proteco Lacq.(revs)	>4000
abrasion penetration Proteco Nat.(revs)	>3500
abrasive wear (mg/100revs)	app. 3,5
Reduction of sound weighted index index "footfall" to the room below. NF EN ISO 140-8 / Acc to NF EN ISO 717-2, ΔL _w in dB with 2 mm Tarkofoam/flex II	17
Formaldehyde emission EN 13986	E1
Reaction to Fire EN 13501	D _{f1}
Thermal insulation value (RT m ² K/W)	
board only	0,101
with rag felt	0,121
with 2 mm Tarkofoam/flex II	0,141
Installation**	Floating / Glue down

Underfloor heating compatible*** Maximum floor surface temperature 27°C with self-regulating under-floor heat system.

* Data show results with new components according to 2006 update.
Method not applicable for brushed products due to the structured surface.

** Contact your flooring supplier for further information.

*** Not suitable for the woodspecies beech and maple.

TANGO

Natura
2-lock
w: 162 mmNatura
2-lock
w: 190 mm

Plank, 13x2000–2200 mm. Minibevel lengthwise.

Oak Eu Nature	•	•
Oak Eu Rustical Brushed		•
Oak Eu Rustical White Brushed	•	

Natura
T-lock
l: 1075 mmNatura
T-lock
l: 1245 mm

Plank, 13x117 mm. Minibevel lengthwise.

Oak Nature		•
Oak Rhapsody Brushed	•	•
Oak Cumin		•
Oak Grey Brushed		•
Oak White Brushed		•

Wood floors, Brinell Hardness (BHN), EN1534

