TEKNISK DATABLAD

Bjelin Herdet tre

Pro Lacquer

BJELIN

Bruksklassifisering private hjem:	**EN ISO 10874** Class Heavy Residential (Class 23)	
Bruksklassifisering offentlige miljø:	**EN ISO 10874** Class Heavy Commercial (Class 33)	

Woodura	Herdet tre
Oppbygning	Bearbeidet herdet treoverflate med HDF-kjerne og stabilserende baksidefinér
Overflatebehandling	UV herdet akrylatlakk

Generelle egenskaper	L
Tykkelse (mm)	9,2 mm
Bredde (mm)	180 mm
Lengde (mm)	2000 mm
Slitesjikt (mm)	0,6 mm
Bord i pakken	7
M^2 2 i pakken	2,5
M^2 pr. pall	90,7
Vekt pr. m^2 (kg)	9
Vekt pr. pakke (kg)	22,7

Klassifisering og teknisk informasjon	Standard test metode	Resultat
Motstandsyktighet mot brann	EN 13501	Bfl-S1 (Begrenset brennbart)
Termisk ledningsevne	EN 12664	0,16 W/(m*K)
Termisk motstand	EN 12667	0,07 (m^2 x K)/W
Formaldehyd emisjon	EN 717-1	E1
Brinellhardhet	EN 1534	8 HB (Gjennomsnittsverdi)
Slagfasthet	EN 14354	EC3
Svellingsgrad	EN 14354	<10%
Slitestyrke	EN14354	>6000 cycles
Sklisikkerhet	CEN/TS 15676	40

Informasjon om installasjon	
Installasjonsmetode	Flytende eller limt ned
Monteringsanvisning	Last ned fra www.bjelin.com
Underlag	Foam/skum med CS > 60 kPa & CC > 20 kPa (i henhold til EN 16354)
Forvaltning, drift og vedlikehold	Last ned fra www.bjelin.com

Copyright ©2023 Bjelin Innovation. Weights and dimensions may have minor variations depending on external circumstances. Bjelin reserves the right to deviate from the weight and dimensions in this technical data sheet.

Licensed by Välinge woodura™ 5G DRY

Woodura and 5G Dry are patented technologies invented by Välinge Innovation AB. The logos are trademarks owned by Välinge Innovation AB and authorized use of such marks are under license.