

**YDEEVNEDEKLARATION****DoP 0238**

til fischer injektionsmørtel FIS V Zero (Flydende fastgørelse til brug i beton)

DA

1. Varetypens unikke identifikationskode:**DoP 0238**2. Anvendelsesformål:**Eftermonteret befæstelse i revnet eller ikke-revnet beton, se appendiks, specifikt Bilage B1 - B10.**3. Fabrikant:**fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Tyskland**4. Bemyndiget repræsentant:**-**5. System(er) til vurdering og kontrol af konstansen af ydeevnen:**1**6. Europæisk vurderingsdokument:**EAD 330499-01-0601, Edition 04/2020**

Europæisk Teknisk Vurdering

Teknisk vurderingsorgan:

Notificeret organ(er)

**ETA-20/0572; 2021-04-28****DIBT- Deutsches Institut für Bautechnik****2873 TU Darmstadt**7. Deklarerer ydeevne(n):**Mekanisk modstand og stabilitet (BWR 1)****Karakteristisk modstand for træklast (statisk og quasi-statisk belastning):**

Modstand overfor stålsvig: Bilag C1 - C3

 $E_s = 210\ 000 \text{ MPa}$ 

Modstand overfor kombineret udtræk og beton-kegle brud: Bilag C4 - C7

 $\tau_{RK,100} = \text{NPD}$ 

Modstand overfor svigt af beton-kegle: Bilag C4

Kantafstand til forhindring af flækning under belastning: Bilag C4

Robusthed: Bilag C4 - C7

Maksimal kærv ved montering: Bilag B3, B4, B6

Min. kant og indbyrdes afstand: Bilag B3 - B6

**Karakteristisk modstand for tværlast (statisk og quasi-statisk belastning):**

Modstand overfor stålsvig: Bilag C1 - C3

Modstand overfor svigt ved udtrækning: Bilag C4

Modstand overfor svigt af betonkant: Bilag C4

**Karakteristisk modstand og Forskydninger for seismiske ydelseskategorier C1 og C2:**

Modstand overfor spændingslast, forskydninger, kategori C1: NPD

Modstand overfor spændingslast, forskydninger, kategori C2: NPD

Modstand overfor tværlast, forskydninger, kategori C1: NPD

Modstand overfor tværlast, forskydninger, kategori C2: NPD

Faktor ringhul: NPD

**Forskydninger under kortvarig og langvarig belastning:**

Forskydninger under kortvarig og langvarig belastning: Bilag C8, C9

**Hygiene, sundhed og miljø (BWR 3)**

Indhold, emission og / eller udledning af farlige stoffer: NPD

8. Relevant teknisk dokumentation og/eller specifik teknisk dokumentation:**-**

Ydeevnen for den vare, der er anført ovenfor, er i overensstemmelse med den deklarerede ydeevne. Denne ydeevnedeklaration er udarbejdet i overensstemmelse med forordning (EU) nr. 305/2011 på eneansvar af den fabrikant, der er anført ovenfor.

Underskrevet for fabrikanten og på dennes vegne af:

Dr. Oliver Geibig, Administrerende direktør Forretningsenheder og ingenørarbejde

Jürgen Grün, Administrerende direktør Kemi &amp; Kvalitet

Tumlingen, 2021-05-12

Denne DoP er tilgængelig i forskellige sprogversioner. I tilfælde af fortolkningsmæssig uoverensstemmelse, henvises der til den engelske version, som altid er gældende.

Appendikset indeholder frivillige og udvidede informationer på engelsk. Disse overgår de lokale (sprognegative) retslige krav.

## **Specific Part**

### **1 Technical description of the product**

The fischer injection system FIS V Zero is a bonded fastener consisting of an injection cartridge with injection mortar FIS V Zero and a steel element according to Annex A.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

### **2 Specification of the intended use in accordance with the applicable European Assessment Document**

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### **3 Performance of the product and references to the methods used for its assessment**

#### **3.1 Mechanical resistance and stability (BWR 1)**

<b>Essential characteristic</b>	<b>Performance</b>
Characteristic resistance to tension load (static and quasi-static loading)	See Annex C 1 to C 7, B 3 to B 6
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C 1 to C 4
Displacements under short-term and long-term loading	See Annex C 8 to C 9
Characteristic resistance and displacements for seismic performance categories C1 and C2	No performance assessed

#### **3.2 Hygiene, health and the environment (BWR 3)**

<b>Essential characteristic</b>	<b>Performance</b>
Content, emission and/or release of dangerous substances	No performance assessed

### **4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base**


In accordance with the European Assessment Document EAD 330499-01-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1


## Installation conditions part 1

fischer anchor rod


Pre-positioned installation



Push through installation (annular gap filled with mortar)



Pre-positioned or push through installation with subsequently injected fischer filling disc  
(annular gap filled with mortar)



Figures not to scale

$h_0$  = drill hole depth

$h_{ef}$  = effective embedment depth

$t_{fix}$  = thickness of fixture

fischer injection system FIS V Zero

**Product description**

Installation conditions part 1


**Annex A 1**

Appendix 2 / 26


## Installation conditions part 2

fischer internal threaded anchor RG M I

### Pre-positioned installation



### Pre-positioned installation with subsequently injected fischer filling disc (annular gap filled with mortar)



Figures not to scale

$h_0$  = drill hole depth

$h_{\text{ef}}$  = effective embedment depth

$t_{\text{fix}}$  = thickness of fixture

fischer injection system FIS V Zero

**Product description**


Installation conditions part 2

**Annex A 2**

Appendix 3 / 26


## Installation conditions part 3

### Reinforcing bar




### fischer rebar anchor FRA

#### Pre-positioned installation



#### Push through installation (annular gap filled with mortar)



Figures not to scale

$h_0$  = drill hole depth

$h_{\text{ef}}$  = effective embedment depth

$t_{\text{fix}}$  = thickness of fixture

$h_{\text{nom}}$  = overall fastener embedment depth in the concrete

fischer injection system FIS V Zero

**Product description**



Installation conditions part 3

**Annex A 3**





Appendix 4 / 26

## Overview system components part 1



**Injection cartridge (shuttle cartridge) with sealing cap; Sizes: 360 ml, 825 ml**





**Imprint:** fischer FIS V Zero, processing notes, shelf-life, piston travel scale (optional), curing times and processing times (depending on temperature), size, volume




**Injection cartridge (coaxial cartridge) with sealing cap; Sizes: 100 ml, 150 ml, 300 ml, 380 ml, 400 ml, 410 ml**




**Imprint:** fischer FIS V Zero, processing notes, shelf-life, piston travel scale (optional), curing times and processing times (depending on temperature), size, volume





**Static mixer FIS MR Plus for injection cartridges up to 410 ml**



**Static mixer FIS JMR for injection cartridges 825 ml**



**Injection adapter and extension tube Ø 9 for static mixer FIS MR Plus;  
Injection adapter and extension tube Ø 9 or Ø 15 for static mixer FIS JMR**



**Cleaning brush BS**



**Blow-out pump**

**AB G**



**ABP:**



Figures not to scale

**fischer injection system FIS V Zero**

**Product description**

Overview system components part 1;  
cartridges / static mixer / accessories

**Annex A 4**

Appendix 5 / 26

## Overview system components part 2

### fischer anchor rod

Size: M8, M10, M12, M16, M20, M24




### fischer internal threaded anchor RG M I


Size: M8, M10, M12, M16



### Screw / threaded rod / washer / hexagon nut



### fischer filling disc with injection adapter



### Reinforcing bar

Nominal diameter:  $\phi 8, \phi 10, \phi 12, \phi 14, \phi 16, \phi 20, \phi 22, \phi 24, \phi 25$



### fischer rebar anchor FRA

Size: M12, M16, M20, M24



Figures not to scale

### fischer injection system FIS V Zero

#### Product description

Overview system components part 2;  
steel components, injection adapter

#### Annex A 5

Appendix 6 / 26

**Table A6.1: Materials**

Part	Designation	Material		
1	Injection cartridge	Mortar, hardener, filler		
Steel grade	Steel	Stainless steel R	High corrosion resistant steel HCR	
	zinc plated	acc. to EN 10088-1:2014 Corrosion resistance class CRC III acc. to EN 1993-1-4:2015	acc. to EN 10088-1:2014 Corrosion resistance class CRC V acc. to EN 1993-1-4:2015	
2	Anchor rod	Property class 4.8, 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$ , ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062, 1.4662, 1.4462; EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50 or 80 EN ISO 3506-1:2009 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529; EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$ , ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529; EN 10088-1:2014
4	Hexagon nut	Property class 4, 5 or 8; EN ISO 898-2:2012 zinc plated $\geq 5 \mu\text{m}$ , ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014
5	fischer internal threaded anchor RG M I	Property class 5.8 ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$ , ISO 4042:2018/Zn5/An(A2K)	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014
6	Commercial standard screw or threaded rod for fischer internal threaded anchor RG M I	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$ , ISO 4042:2018/Zn5/An(A2K) $A_5 > 8\%$ fracture elongation	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014 $A_5 > 8\%$ fracture elongation	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014 $A_5 > 8\%$ fracture elongation
7	fischer filling disc similar to DIN 6319-G	zinc plated $\geq 5 \mu\text{m}$ , ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529; EN 10088-1:2014
8	Reinforcing bar EN 1992-1-1:2004 and AC:2010, Annex C	Bars and de-coiled rods, class B or C with $f_{yk}$ and k according to NDP or NCL of according to EN 1992-1-1/NA $f_{uk} = f_{ik} = K \cdot f_{yk}$ ( $A_5 > 8\%$ )		
9	fischer rebar anchor FRA	Rebar part: Bars and de-coiled rods class B or C with $f_{yk}$ and k according to NDP or NCL of EN 1992-1-1:2004+AC:2010 $f_{uk} = f_{ik} = K \cdot f_{yk}$	Threaded part: Property class 70 or for M24 PC 80, EN ISO 3506-1:2009 1.4401, 1.4404, 1.4571, 1.4578, 1.4439, 1.4362, 1.4062 acc. to EN 10088-1:2014 Corrosion resistance class CRC III acc. to EN 1993-1-4:2015 1.4565; 1.4529 acc. to EN 10088-1:2014 Corrosion resistance class CRC V acc. to EN 1993-1-4:2015	
fischer injection system FIS V Zero				
<b>Product description</b> Materials			<b>Annex A 6</b> Appendix 7 / 26	

## **Specifications of intended use (part 1)**

**Table B1.1:** Overview use and performance categories

## **Specifications of intended use (part 2)**

### **Base materials:**

- Compacted reinforced or unreinforced normal weight concrete without fibres of strength classes C20/25 to C50/60 according to EN 206:2013+A1:2016

### **Use conditions (Environmental conditions):**

- Structures subject to dry internal conditions (zinc plated steel, stainless steel or high corrosion resistant steel).
- For all other conditions according to EN 1993-1-4:2015 corresponding to corrosion resistance classes to Annex A 6 table A6.1.

### **Design:**

- Anchorages have to be designed by a responsible engineer with experience of concrete anchor design.
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed in accordance with:  
EN 1992-4:2018 and EOTA Technical Report TR 055, Edition February 2018.

### **Installation:**

- Anchor installation is to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- In case of aborted hole: The hole shall be filled with mortar
- Anchorage depth should be marked and adhered to installation
- Overhead installation is allowed (necessary equipment see installation instruction)

fischer injection system FIS V Zero

**Intended use**  
Specifications (part 2)


**Annex B 2**

Appendix 9 / 26

**Table B3.1:** Installation parameters for anchor rods

Anchor rods	Thread	M8	M10	M12	M16	M20	M24
Width across flats	SW	13	17	19	24	30	36
Nominal drill hole diameter	$d_0$	10	12	14	18	22	28
Drill hole depth	$h_0$	$h_0 = h_{\text{ef}}$					
Effective embedment depth	$h_{\text{ef, min}}$ $h_{\text{ef, max}}$	60	60	70	80	90	96
Minimum spacing and minimum edge distance	$s_{\text{min}} = c_{\text{min}}$	160	200	240	320	400	480
Diameter of the clearance hole of the fixture	pre-positioned installation push through installation	40	45	55	65	85	105
Minimum thickness of concrete member	$h_{\text{min}}$	9	12	14	18	22	26
Maximum installation torque	max $T_{\text{inst}}$ [Nm]	12	14	16	20	24	30
$h_{\text{ef}} + 30 (\geq 100)$				$h_{\text{ef}} + 2d_0$			

### fischer anchor rod




### Marking (on random place) fischer anchor rod:

Steel zinc plated PC <sup>1)</sup> 8.8	• or +	Steel hot-dip PC <sup>1)</sup> 8.8	•
High corrosion resistant steel HCR PC <sup>1)</sup> 50	•	High corrosion resistant steel HCR PC <sup>1)</sup> 70	-
High corrosion resistant steel HCR PC <sup>1)</sup> 80	(	Stainless steel R property class 50	~
Stainless steel R property class 80	*		

Alternatively: Colour coding according to DIN 976-1: 2016

<sup>1)</sup> PC = property class

### Installation conditions:



**Commercial standard threaded rods, washers and hexagon nuts may also be used, if the following requirements are fulfilled:**

- Materials, dimensions and mechanical properties according to Annex A 6, Table A6.1
- Inspection certificate 3.1 according to EN 10204:2004, the documents have to be stored
- Setting depth is marked

Figures not to scale

fischer injection system FIS V Zero


**Intended use**  
Installation parameters anchor rods

**Annex B 3**

**Table B4.1:** Installation parameters for fischer internal threaded anchors RG M I

Internal threaded anchors RG M I	Thread	M8	M10	M12	M16
Diameter of anchor $d_{\text{nom}} = d_H$	[mm]	12	16	18	22
Nominal drill hole diameter $d_0$		14	18	20	24
Drill hole depth $h_0$		$h_0 = h_{\text{ef}} = L_H$			
Effective embedment depth $(h_{\text{ef}} = L_H)$		90	90	125	160
Minimum spacing and minimum edge distance $s_{\text{min}} = c_{\text{min}}$		55	65	75	95
Diameter of clearance hole in the fixture $d_f$		9	12	14	18
Minimum thickness of concrete member $h_{\text{min}}$		120	125	165	205
Maximum screw-in depth $l_{E,\text{max}}$		18	23	26	35
Minimum screw-in depth $l_{E,\text{min}}$		8	10	12	16
Maximum installation torque $\text{max } T_{\text{inst}}$	[Nm]	10	20	40	80

**fischer internal threaded anchor RG M I**




**Marking:** Anchor size e. g.: **M10**

Stainless steel → additional **R**; e.g.: **M10 R**

High corrosion resistant steel → additional **HCR**; e.g.: **M10 HCR**

Retaining bolt or threaded rods (including nut and washer) must comply with the appropriate material and strength class of Annex A 6, Table A6.1

**Installation conditions:**



Figures not to scale

fischer injection system FIS V Zero

**Intended use**

Installation parameters internal threaded anchors RG M I

**Annex B 4**

**Table B5.1:** Installation parameters for **reinforcing bars**

Nominal diameter of the bar	$\phi$	8 <sup>1)</sup>	10 <sup>1)</sup>	12 <sup>1)</sup>	14	16	20	22	24	25
Nominal drill hole diameter	d <sub>0</sub>	10	12	12	14	14	16	18	20	25
Drill hole depth								h <sub>0</sub> = h <sub>ef</sub>	28	30
Effective embedment depth		60	60	70	75	80	90	94	98	100
		160	200	240	280	320	400	440	480	500
Minimum spacing and minimum edge distance		40	45	55	60	65	85	95	105	110
Minimum thickness of concrete member		h <sub>ef</sub> + 30 (≥ 100)			h <sub>ef</sub> + 2d <sub>0</sub>					


<sup>1)</sup> Both drill hole diameters can be used

#### Reinforcing bar



- The minimum value of related rib area  $f_{R,min}$  must fulfil the requirements of EN 1992-1-1:2004+AC:2010
- The rib height must be within the range:  $0,05 \cdot \phi \leq h_{rib} \leq 0,07 \cdot \phi$   
( $\phi$  = Nominal diameter of the bar,  $h_{rib}$  = rib height)

#### Installation conditions:



Figures not to scale

fischer injection system FIS V Zero

**Intended use**  
Installation parameters reinforcing bars


**Annex B 5**

**Table B6.1:** Installation parameters for fischer rebar anchor FRA

Rebar anchor FRA	Thread	M12 <sup>1)</sup>	M16	M20	M24
Nominal diameter of the bar $\phi$	[mm]	12	16	20	25
Width across flats SW		19	24	30	36
Nominal drill hole diameter $d_0$		14	16	20	25
Drill hole depth $h_0$		$h_{\text{ef}} + l_e$			
Effective embedment depth $\frac{h_{\text{ef},\text{min}}}{h_{\text{ef},\text{max}}}$		70	80	90	96
Distance concrete surface to welded joint $l_e$		140	220	300	380
Minimum spacing and minimum edge distance $s_{\text{min}} = c_{\text{min}}$		100			
Diameter of clearance hole in the fixture $\leq d_f$		55	65	85	105
push through anchorage $\leq d_f$		14	18	22	26
Minimum thickness of concrete member $h_{\text{min}}$		18	22	26	32
Maximum installation torque $\text{max } T_{\text{inst}}$ [Nm]	$h_0 + 30$	$h_0 + 2d_0$			

<sup>1)</sup> Both drill hole diameters can be used

### fischer rebar anchor FRA




Marking frontal e.g.:

FRA (for stainless steel);

FRA HCR (for high corrosion resistant steel)

### Installation conditions:



Figures not to scale

fischer injection system FIS V Zero

### Intended use


Installation parameters fischer rebar anchor FRA

### Annex B 6

**Table B7.1:** Parameters of the **cleaning brush BS** (steel brush with steel bristles)

The size of the cleaning brush refers to the drill hole diameter

Nominal drill hole diameter	$d_0$	[mm]	10	12	14	16	18	20	22	24	25	28	30	
Steel brush diameter	$d_b$		11	14	16		20		25		26	27	30	40

**Table B7.2:** Conditions for use **static mixer** without an **extension tube**

Nominal drill hole diameter	$d_0$	[mm]	10	12	14	16	18	20	22	24	25	28	30
Drill hole depth $h_0$ by FIS MR Plus using FIS JMR		[mm]	$\leq 90$	$\leq 120$	$\leq 140$	$\leq 150$	$\leq 160$	$\leq 170$	$\leq 190$			$\leq 210$	

**Table B7.3** **Maximum processing** time of the mortar and **minimum curing** time  
(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature)

Temperature at anchoring base [°C]	Maximum processing time $t_{work}$	Minimum curing time <sup>1)</sup> $t_{cure}$
	FIS V Zero	FIS V Zero
-10 to -5 <sup>2)</sup>	6 h	72 h
> -5 to 0 <sup>2)</sup>	2 h	24 h
> 0 to 5 <sup>2)</sup>	45 min	12 h
> 5 to 10	20 min	6 h
> 10 to 15	8 min	3 h
> 15 to 20	5 min	2 h
> 20 to 25	3 min	1 h
> 25 to 30	2 min	45 min
> 30 to 40	1 min	30 min

<sup>1)</sup> In wet concrete or water filled holes the curing times must be doubled<sup>2)</sup> Minimum cartridge temperature +5°C

fischer injection system FIS V Zero

**Intended use**

Cleaning brush (steel brush)

Processing time and curing time

**Annex B 7**

## Installation instructions part 1

Drilling and cleaning the hole (hammer drilling with standard drill bit)

1		Drill the hole. Nominal drill hole diameter $d_0$ and drill hole depth $h_0$ see <b>tables B3.1, B4.1, B5.1, B6.1</b>		
2		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18$ mm blow out the hole twice by hand		For $h_{ef} > 12d$ and / or $d_0 \geq 18$ mm blow out the hole twice with oil-free compressed air ( $p \geq 6$ bar)
3		Brush the drill hole twice. For drill hole diameter $d_0 \geq 18$ mm and / or $h_{ef} > 12d$ use a power drill. For deep holes use an extension. Corresponding brushes see <b>table B7.1</b>		
4		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18$ mm blow out the hole twice by hand		For $h_{ef} > 12d$ and / or $d_0 \geq 18$ mm blow out the hole twice with oil-free compressed air ( $p \geq 6$ bar)

Go to step 5

Drilling and cleaning the hole (hammer drilling with hollow drill bit)

1		Check a suitable hollow drill (see <b>table B1.1</b> ) for correct operation of the dust extraction
2		Use a suitable dust extraction system, e.g. fischer FVC 35 M or a comparable dust extraction system with equivalent performance data  Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. Nominal drill hole diameter $d_0$ and drill hole depth $h_0$ see <b>tables B3.1, B4.1, B5.1, B6.1</b>

Go to step 5

fischer injection system FIS V Zero

Intended use


Installation instructions part 1

Annex B 8

Appendix 15 / 26


## Installation instructions part 2

### Preparing the cartridge

5		Remove the sealing cap Screw on the static mixer (the spiral in the static mixer must be clearly visible)
6		Place the cartridge into the dispenser
7		Extrude approximately 10 cm of material out until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey

Go to step 8

### Injection of the mortar

8		<p>Fill approximately 2/3 of the drill hole with mortar. Always begin from the bottom of the hole and avoid bubbles</p> <p>The conditions for mortar injection without extension tube can be found in <b>table B7.2</b>. For deeper drill holes, than those mentioned in <b>table B7.2</b>, use a suitable extension tube</p> <p>For overhead installation, deep holes (<math>h_0 &gt; 250</math> mm) or drill hole diameter (<math>d_0 = 30</math> mm) use an injection adapter</p>
---	---	--

Go to step 9

fischer injection system FIS V Zero

**Intended use**






Installation instructions part 2

**Annex B 9**



Appendix 16 / 26

## Installation instructions part 3

### Installation of anchor rods or fischer internal threaded anchors RG M I

9			<p>Only use clean and oil-free metal parts. Mark the setting depth of the metal part. Push the anchor rod or fischer internal threaded RG M I anchor down to the bottom of the hole, turning it slightly while doing so. After inserting the metal parts, excess mortar must be emerged around the anchor element.</p>	
		<p>For overhead installations support the metal part with wedges (e.g. fischer centering wedges) or fischer overhead clips.</p>		
10		<p>Wait for the specified curing time <math>t_{\text{cure}}</math> see <b>table B7.3</b></p>		11
Option		<p>After the minimum curing time is reached, the gap between metal part and fixture (annular clearance) may be filled with mortar via the fischer filling disc. Compressive strength <math>\geq 50 \text{ N/mm}^2</math> (e.g. fischer injection mortars FIS V Zero, FIS HB, FIS SB, FIS V, FIS V Plus, FIS EM Plus). <b>ATTENTION:</b> Using fischer filling disc reduces <math>t_{\text{fix}}</math> (usable length of the anchor)</p>		Mounting the fixture $\text{max } T_{\text{inst}}$ see <b>tables B3.1 and B4.1</b>

### Installation reinforcing bars and fischer rebar anchor FRA

9		<p>Only use clean and oil-free reinforcing bars or fischer rebar anchor FRA. Mark the setting depth. Push the reinforcement bar or the fischer rebar anchor FRA into the filled hole up to the setting depth mark. <b>Recommendation:</b> Rotation back and forth of the reinforcement bar or the fischer rebar anchor FRA makes pushing easy</p>		
		<p>When the setting depth mark is reached, excess mortar must be emerged from the mouth of the drill hole.</p>		
10		Wait for the specified curing time $t_{\text{cure}}$ see <b>table B7.3</b>	11	Mounting the fixture $\text{max } T_{\text{inst}}$ see <b>table B6.1</b>

fischer injection system FIS V Zero

**Intended use**

Installation instructions part 3

**Annex B 10**

Appendix 17 / 26

**Table C1.1: Characteristic values for steel failure under tension / shear load of fischer anchor rods and standard threaded rods**

Anchor rod / standard threaded rod			M8	M10	M12	M16	M20	M24	
<b>Bearing capacity under tension load, steel failure <sup>3)</sup></b>									
Characteristic resistance $N_{Rk,s}$	Property class	4.8	15(13)	23(21)	33	63	98	141	
		5.8	19(17)	29(27)	43	79	123	177	
		8.8	29(27)	47(43)	68	126	196	282	
		50	19	29	43	79	123	177	
		70	26	41	59	110	172	247	
		80	30	47	68	126	196	282	
		[kN]							
<b>Partial factors <sup>1)</sup></b>									
Partial factor $\gamma_{Ms,N}$	Property class	4.8				1,50			
		5.8				1,50			
		8.8				1,50			
		50				2,86			
		70				1,50 <sup>2)</sup> / 1,87			
		80				1,60			
		[ $\cdot$ ]							
<b>Bearing capacity under shear load, steel failure <sup>3)</sup></b>									
<b>without lever arm</b>									
Characteristic resistance $V_{Rk,s}^0$	Property class	4.8	9(8)	14(13)	20	38	59	85	
		5.8	11(10)	17(16)	25	47	74	106	
		8.8	15(13)	23(21)	34	63	98	141	
		50	9	15	21	39	61	89	
		70	13	20	30	55	86	124	
		80	15	23	34	63	98	141	
		[kN]							
Ductility factor	k <sub>7</sub>	[ $\cdot$ ]				1,0			
<b>with lever arm</b>									
Characteristic resistance $M_{Rk,s}^0$	Property class	4.8	15(13)	30(27)	52	133	259	448	
		5.8	19(16)	37(33)	65	166	324	560	
		8.8	30(26)	60(53)	105	266	519	896	
		50	19	37	65	166	324	560	
		70	26	52	92	232	454	784	
		80	30	60	105	266	519	896	
		[Nm]							
<b>Partial factors <sup>1)</sup></b>									
Partial factor $\gamma_{Ms,V}$	Property class	4.8				1,25			
		5.8				1,25			
		8.8				1,25			
		50				2,38			
		70				1,25 <sup>2)</sup> / 1,56			
		80				1,33			
		[ $\cdot$ ]							

<sup>1)</sup> In absence of other national regulations

2) Only admissible for high corrosion resist. steel HCR, with  $f_{ck} / f_{ck}^{\text{ref}} \geq 0.8$  and  $A_s > 12\%$  (e.g. fischer anchor rods).

<sup>3)</sup> Values in brackets are valid for undersized threaded rods with smaller stress area  $A_s$  for hot dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009.

fischer injection system FIS V Zero

### **Performances**

Characteristic values for steel failure under tension / shear load of fischer anchor rods and standard threaded rods

Annex C 1

**Table C2.1: Characteristic values for steel failure under tension / shear load of fischer internal threaded anchors RG M I**

fischer internal threaded anchors RG M I			M8	M10	M12	M16		
<b>Bearing capacity under tension load, steel failure</b>								
Charact. resistance with screw	$N_{Rk,s}$	Property class	5.8	[kN]	19	29	43	79
		Property class	8.8		29	47	68	108
		Property class	R		26	41	59	110
		Property class 70	HCR		26	41	59	110
<b>Partial factors<sup>1)</sup></b>								
Partial factors	$\gamma_{Ms,N}$	Property class	5.8	[-]	1,50			
		Property class	8.8		1,50			
		Property class	R		1,87			
		Property class 70	HCR		1,87			
<b>Bearing capacity under shear load, steel failure</b>								
<b>Without lever arm</b>								
Charact. resistance with screw	$V^0_{Rk,s}$	Property class	5.8	[kN]	9,2	14,5	21,1	39,2
		Property class	8.8		14,6	23,2	33,7	54,0
		Property class	R		12,8	20,3	29,5	54,8
		Property class 70	HCR		12,8	20,3	29,5	54,8
Ductility factor		$k_7$	[-]		1,0			
<b>With lever arm</b>								
Charact. resistance with screw	$M^0_{Rk,s}$	Property class	5.8	[Nm]	20	39	68	173
		Property class	8.8		30	60	105	266
		Property class	R		26	52	92	232
		Property class 70	HCR		26	52	92	232
<b>Partial factors<sup>1)</sup></b>								
Partial factors	$\gamma_{Ms,V}$	Property class	5.8	[-]	1,25			
		Property class	8.8		1,25			
		Property class	R		1,56			
		Property class 70	HCR		1,56			
<sup>1)</sup> In absence of other national regulations								
fischer injection system FIS V Zero								
<b>Performances</b> Characteristic values for steel failure under tension / shear load of fischer internal threaded anchor RG M I					<b>Annex C 2</b> Appendix 19 / 26			

**Table C3.1:** Characteristic values for steel failure under tension / shear load of reinforcing bars

Nominal diameter of the bar	$\phi$	8	10	12	14	16	20	22	24	25								
<b>Bearing capacity under tension load, steel failure</b>																		
Characteristic resistance	$N_{Rk,s}$ [kN]	$A_s \cdot f_{uk}^{(2)}$																
<b>Bearing capacity under shear load, steel failure</b>																		
<b>Without lever arm</b>																		
Characteristic resistance	$V_{Rk,s}^0$ [kN]	$k_6^{(1)} \cdot A_s \cdot f_{uk}^{(2)}$																
Ductility factor	$k_7$ [-]	1,0																
<b>With lever arm</b>																		
Characteristic resistance	$M_{Rk,s}^0$ [Nm]	1,2 $\cdot W_{el} \cdot f_{uk}^{(2)}$																

- <sup>1)</sup> In accordance with EN 1992-4:2018 section 7.2.2.3.1
  - $k_6 = 0,6$  for fasteners made of carbon steel with  $f_{uk} \leq 500 \text{ N/mm}^2$
  - $= 0,5$  for fasteners made of carbon steel with  $500 < f_{uk} \leq 1000 \text{ N/mm}^2$
  - $= 0,5$  for fasteners made of stainless steel
- <sup>2)</sup>  $f_{uk}$  or  $f_{yk}$  respectively must be taken from the specifications of the reinforcing bar

**Table C3.2:** Characteristic values for steel failure under tension / shear load of fischer rebar anchors FRA

fischer rebar anchor FRA		M12	M16	M20	M24				
<b>Bearing capacity under tension load, steel failure</b>									
Characteristic resistance	$N_{Rk,s}$ [kN]	59	110	172	270				
<b>Partial factor<sup>1)</sup></b>									
Partial factor	$\gamma_{Ms,N}$ [-]	1,4							
<b>Bearing capacity under shear load, steel failure</b>									
<b>Without lever arm</b>									
Characteristic resistance	$V_{Rk,s}^0$ [kN]	30	55	86	141				
Ductility factor	$k_7$ [-]	1,0							
<b>With lever arm</b>									
Characteristic resistance	$M_{Rk,s}^0$ [Nm]	92	233	454	898				
<b>Partial factor<sup>1)</sup></b>									
Partial factor	$\gamma_{Ms,V}$ [-]	1,56							

<sup>1)</sup> In absence of other national regulations

### fischer injection system FIS V Zero

#### Performances

Characteristic values for steel failure under tension / shear load of reinforcing bars and fischer rebar anchors FRA

#### Annex C 3

**Table C4.1:** Characteristic values for **concrete failure** under **tension / shear load**

Size		All sizes						
<b>Tension load</b>								
Installation factor	$\gamma_{\text{inst}}$	[ - ]	See annex C 5 to C 8					
<b>Factors for the compressive strength of concrete &gt; C20/25</b>								
Increasing factor for $\tau_{\text{RK}}$	C25/30	$\Psi_c$	[ - ]	1,03				
	C30/37			1,06				
	C35/45			1,09				
	C40/50			1,11				
	C45/55			1,13				
	C50/60			1,15				
<b>Splitting failure</b>								
Edge distance	$h / h_{\text{ef}} \geq 2,0$	$c_{\text{cr,sp}}$	[mm]	1,0 $h_{\text{ef}}$				
	$2,0 > h / h_{\text{ef}} > 1,3$			4,6 $h_{\text{ef}}$ - 1,8 $h$				
	$h / h_{\text{ef}} \leq 1,3$			2,26 $h_{\text{ef}}$				
Spacing	$s_{\text{cr,sp}}$			2 $c_{\text{cr,sp}}$				
<b>Concrete cone failure</b>								
Uncracked concrete	$k_{\text{ucr,N}}$	[ - ]	[mm]	11,0				
Cracked concrete	$k_{\text{cr,N}}$			7,7				
Edge distance	$c_{\text{cr,N}}$	[mm]		1,5 $h_{\text{ef}}$				
Spacing	$s_{\text{cr,N}}$			2 $c_{\text{cr,N}}$				
<b>Factors for sustained tension load</b>								
Temperature range		[ - ]		24 °C / 40 °C		50 °C / 80 °C		72 °C / 120 °C
Factor	$\psi_{\text{sus}}^0$	[ - ]		0,67		0,67		0,75
<b>Shear load</b>								
Installation factor	$\gamma_{\text{inst}}$	[ - ]		1,0				
<b>Concrete pry-out failure</b>								
Factor for pry-out failure	$k_8$	[ - ]		2,0				
<b>Concrete edge failure</b>								
Effective length of fastener in shear loading	$l_f$	[mm]		for $d_{\text{nom}} \leq 24 \text{ mm}$ : min ( $h_{\text{ef}}$ ; 12 $d_{\text{nom}}$ ) for $d_{\text{nom}} > 24 \text{ mm}$ : min ( $h_{\text{ef}}$ ; 8 $d_{\text{nom}}$ ; 300 mm)				
<b>Calculation diameters</b>								
Size			M8	M10	M12	M16	M20	M24
fischer anchor rods and standard threaded rods	$d_{\text{nom}}$	[mm]	8	10	12	16	20	24
fischer internal threaded anchors RG M I	$d_{\text{nom}}$		12	16	18	22	-1)	-1)
fischer rebar anchor FRA	$d_{\text{nom}}$		-1)	-1)	12	16	20	25
Size (nominal diameter of the bar)	$\phi$	8	10	12	14	16	20	22
Reinforcing bar	$d_{\text{nom}}$	[mm]	8	10	12	14	16	20
1) Anchor type not part of the assessment								
fischer injection system FIS V Zero							<b>Annex C 4</b>	
Performances Characteristic values for concrete failure under tension / shear load								Appendix 21 / 26

**Table C5.1:** Characteristic values for **combined pull-out and concrete failure** for **fischer anchor rods and standard threaded rods** in hammer drilled holes; **uncracked or cracked concrete**

Anchor rod / standard threaded rod		M8	M10	M12	M16	M20	M24					
<b>Combined pullout and concrete cone failure</b>												
Calculation diameter	d [mm]	8	10	12	16	20	24					
<b>Uncracked concrete</b>												
<b>Characteristic bond resistance in uncracked concrete C20/25</b>												
Hammer-drilling with standard drill bit (dry or wet concrete, water filled hole)												
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$ [N/mm <sup>2</sup> ]	10	10	10	10	9,5	8,5				
	II: 50 °C / 80 °C		10	10	10	10	9,5	8,5				
	III: 72 °C / 120 °C		8	8	8	8	8	7				
Hammer-drilling with hollow drill bit (dry or wet concrete)												
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$ [N/mm <sup>2</sup> ]	- <sup>1)</sup>	6,5	6	6	6	5				
	II: 50 °C / 80 °C		- <sup>1)</sup>	6,5	6	6	6	5				
	III: 72 °C / 120 °C		- <sup>1)</sup>	5,5	5	5	5	4,5				
<b>Installation factors</b>												
Dry or wet concrete and water filled hole	$\gamma_{inst}$	[-]	1,4									
<b>Cracked concrete</b>												
<b>Characteristic bond resistance in cracked concrete C20/25</b>												
Hammer-drilling with standard drill bit (dry or wet concrete, water filled hole)												
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,cr}$ [N/mm <sup>2</sup> ]	4	4	4	4	4	4				
	II: 50 °C / 80 °C		4	4	4	4	4	4				
	III: 72 °C / 120 °C		3	3	3,5	3,5	3,5	3,5				
<b>Installation factors</b>												
Dry or wet concrete and water filled hole	$\gamma_{inst}$	[-]	1,4									
<sup>1)</sup> No performance assessed												
fischer injection system FIS V Zero												
<b>Performances</b> Characteristic values for combined pull-out and concrete failure for fischer anchor rod and standard threaded rods						<b>Annex C 5</b> Appendix 22 / 26						

**Table C6.1:** Characteristic values for **combined pull-out and concrete failure** for **fischer internal threaded anchors RG M 1** in hammer drilled holes; **uncracked or cracked concrete**

Internal threaded anchor RG M 1		M8	M10	M12	M16			
<b>Combined pullout and concrete cone failure</b>								
Calculation diameter	d [mm]	12	16	18	22			
<b>Uncracked concrete</b>								
<b>Characteristic bond resistance in uncracked concrete C20/25</b>								
<u>Hammer-drilling with standard drill bit (dry or wet concrete, water filled hole)</u>								
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$ [N/mm <sup>2</sup> ]	7,5	7,5	7,5			
	II: 50 °C / 80 °C		7,5	7,5	7,5			
	III: 72 °C / 120 °C		6,5	6,5	6,5			
<u>Hammer-drilling with hollow drill bit (dry or wet concrete)</u>								
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$ [N/mm <sup>2</sup> ]	6,5	6,5	6,5			
	II: 50 °C / 80 °C		6,5	6,5	6,5			
	III: 72 °C / 120 °C		5,5	5,5	5,5			
<b>Installation factors</b>								
Dry or wet concrete and water filled hole	$\gamma_{inst}$	[-]	1,4					
<b>Cracked concrete</b>								
<b>Characteristic bond resistance in cracked concrete C20/25</b>								
<u>Hammer-drilling with standard drill bit (dry or wet concrete, water filled hole)</u>								
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,cr}$ [N/mm <sup>2</sup> ]	4,5	4	4			
	II: 50 °C / 80 °C		4,5	4	4			
	III: 72 °C / 120 °C		3,5	3,5	3			
<b>Installation factors</b>								
Dry or wet concrete and water filled hole	$\gamma_{inst}$	[-]	1,4					
<b>fischer injection system FIS V Zero</b>								
<b>Performances</b> Characteristic values for combined pull-out and concrete failure for fischer internal threaded anchors RG M 1				<b>Annex C 6</b> Appendix 23 / 26				

**Table C7.1:** Characteristic values for **combined pull-out and concrete failure** for **reinforcing bars** in hammer drilled holes; **uncracked concrete**

Nominal diameter of the bar	$\phi$	8	10	12	14	16	20	22	24	25
<b>Combined pullout and concrete cone failure</b>										
Calculation diameter	d [mm]	8	10	12	14	16	20	22	24	25
<b>Uncracked concrete</b>										
<b>Characteristic bond resistance in uncracked concrete C20/25</b>										
Hammer-drilling with standard drill bit (dry or wet concrete, water filled hole)										
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$ [N/mm <sup>2</sup> ]	6,5	7	7	7,5	7,5	8	8	8
	II: 50 °C / 80 °C		6,5	7	7	7,5	7,5	8	8	8
	III: 72 °C / 120 °C		5,5	5,5	6	6	6,5	6,5	6,5	6,5
Hammer-drilling with hollow drill bit (dry or wet concrete)										
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$ [N/mm <sup>2</sup> ]	6	6	6	6	6	6	5,5	5,5
	II: 50 °C / 80 °C		6	6	6	6	6	6	5,5	5,5
	III: 72 °C / 120 °C		5	5	5	5	5	5	4,5	4,5
<b>Installation factors</b>										
Dry or wet concrete and water filled hole	$\gamma_{inst}$	[ $-$ ]	1,4							

**Table C7.2:** Characteristic values for **combined pull-out and concrete failure** for **fischer rebar anchors FRA** in hammer drilled holes; **uncracked concrete**

fischer rebar anchors FRA	M12	M16	M20	M24		
<b>Combined pullout and concrete cone failure</b>						
Calculation diameter	d [mm]	12	16	20	25	
<b>Uncracked concrete</b>						
<b>Characteristic bond resistance in uncracked concrete C20/25</b>						
Hammer-drilling with standard drill bit (dry or wet concrete, water filled hole)						
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$ [N/mm <sup>2</sup> ]	7	7,5	8	8
	II: 50 °C / 80 °C		7	7,5	8	8
	III: 72 °C / 120 °C		6	6,5	6,5	6,5
Hammer-drilling with hollow drill bit (dry or wet concrete)						
Tem- pera ture range	I: 24 °C / 40 °C	$\tau_{Rk,ucr}$ [N/mm <sup>2</sup> ]	6	6	6	5,5
	II: 50 °C / 80 °C		6	6	6	5,5
	III: 72 °C / 120 °C		5	5	5	4,5
<b>Installation factors</b>						
Dry or wet concrete and water filled hole	$\gamma_{inst}$	[ $-$ ]	1,4			

fischer injection system FIS V Zero

#### Performances

Characteristic values for combined pull-out and concrete failure for reinforcing bars and fischer rebar anchor FRA

**Annex C 7**

**Table C8.1: Displacements for anchor rods**

Anchor rod	M8	M10	M12	M16	M20	M24
<b>Displacement-Factors for tension load<sup>1)</sup></b>						
<b>Uncracked concrete; Temperature range I, II, III</b>						
δN₀-Factor [mm/(N/mm²)]	0,04	0,04	0,05	0,06	0,07	0,08
δN∞-Factor	0,04	0,04	0,05	0,06	0,07	0,08
<b>Cracked concrete; Temperature range I, II, III</b>						
δN₀-Factor [mm/(N/mm²)]	0,10	0,11	0,11	0,13	0,14	0,16
δN∞-Factor	0,10	0,11	0,11	0,13	0,14	0,16
<b>Displacement-Factors for shear load<sup>2)</sup></b>						
<b>Uncracked or cracked concrete; Temperature range I, II, III</b>						
δV₀-Factor [mm/kN]	0,18	0,15	0,12	0,09	0,07	0,06
δV∞-Factor	0,27	0,22	0,18	0,14	0,11	0,09

1) Calculation of effective displacement:

$$\delta N_0 = \delta N_0\text{-Factor} \cdot \tau_{Ed}$$

$$\delta N_\infty = \delta N_\infty\text{-Factor} \cdot \tau_{Ed}$$

( $\tau_{Ed}$ : Design value of the applied tensile bond stress)

2) Calculation of effective displacement:

$$\delta V_0 = \delta V_0\text{-Factor} \cdot V_{Ed}$$

$$\delta V_\infty = \delta V_\infty\text{-Factor} \cdot V_{Ed}$$

( $V_{Ed}$ : Design value of the applied shear force)

**Table C8.2: Displacements for fischer internal threaded anchors RG M I**

Internal threaded anchor RG M I	M8	M10	M12	M16
<b>Displacement-Factors for tension load<sup>1)</sup></b>				
<b>Uncracked concrete; Temperature range I, II, III</b>				
δN₀-Factor [mm/(N/mm²)]	0,06	0,07	0,07	0,07
δN∞-Factor	0,06	0,07	0,07	0,07
<b>Cracked concrete; Temperature range I, II, III</b>				
δN₀-Factor [mm/(N/mm²)]	0,10	0,11	0,11	0,12
δN∞-Factor	0,10	0,11	0,11	0,12
<b>Displacement-Factors for shear load<sup>2)</sup></b>				
<b>Uncracked or cracked concrete; Temperature range I, II, III</b>				

δV₀-Factor [mm/kN]	0,12	0,09	0,08	0,07
δV∞-Factor	0,18	0,14	0,12	0,10

1) Calculation of effective displacement:

$$\delta N_0 = \delta N_0\text{-Factor} \cdot \tau_{Ed}$$

$$\delta N_\infty = \delta N_\infty\text{-Factor} \cdot \tau_{Ed}$$

( $\tau_{Ed}$ : Design value of the applied tensile bond stress)

2) Calculation of effective displacement:

$$\delta V_0 = \delta V_0\text{-Factor} \cdot V_{Ed}$$

$$\delta V_\infty = \delta V_\infty\text{-Factor} \cdot V_{Ed}$$

( $V_{Ed}$ : Design value of the applied shear force)

fischer injection system FIS V Zero

#### Performances

Displacements for anchor rods and fischer internal threaded anchor rods

#### Annex C 8

**Table C9.1: Displacements for reinforcing bars**

Nominal diameter of the bar	$\Phi$	8	10	12	14	16	20	22	24	25
<b>Displacement-Factors for tension load<sup>1)</sup></b>										
<b>Uncracked concrete; Temperature range I, II, III</b>										
$\delta_{N0}$ -Factor	[mm/(N/mm <sup>2</sup> )]	0,05	0,06	0,07	0,08	0,09	0,10	0,11	0,12	0,12
$\delta_{N\infty}$ -Factor		0,05	0,06	0,07	0,08	0,09	0,10	0,11	0,12	0,12
<b>Displacement-Factors for shear load<sup>2)</sup></b>										
<b>Uncracked concrete; Temperature range I, II, III</b>										
$\delta_{V0}$ -Factor	[mm/kN]	0,18	0,15	0,12	0,10	0,09	0,07	0,07	0,06	0,06
$\delta_{V\infty}$ -Factor		0,27	0,22	0,18	0,16	0,14	0,11	0,10	0,09	0,09

1) Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

( $\tau_{Ed}$ : Design value of the applied tensile bond stress)

2) Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

( $V_{Ed}$ : Design value of the applied shear force)

**Table C9.2: Displacements for fischer rebar anchors FRA**

fischer rebar anchor FRA	M12	M16	M20	M24	
<b>Displacement-Factors for tension load<sup>1)</sup></b>					
<b>Uncracked concrete; Temperature range I, II, III</b>					
$\delta_{N0}$ -Factor	[mm/(N/mm <sup>2</sup> )]	0,07	0,09	0,10	0,12
$\delta_{N\infty}$ -Factor		0,07	0,09	0,10	0,12
<b>Displacement-Factors for shear load<sup>2)</sup></b>					
<b>Uncracked concrete; Temperature range I, II, III</b>					
$\delta_{V0}$ -Factor	[mm/kN]	0,12	0,09	0,07	0,06
$\delta_{V\infty}$ -Factor		0,18	0,14	0,11	0,09

1) Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

( $\tau_{Ed}$ : Design value of the applied tensile bond stress)

2) Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

( $V_{Ed}$ : Design value of the applied shear force)

fischer injection system FIS V Zero

#### Performances

Displacements for reinforcing bars and fischer rebar anchors FRA

#### Annex C 9